salesusa@ccewool.comwww.ccewool.com

CCEWOOL® Ceramic Fiber Paper



Temperature Grade 1260 $^{\circ}$ C (2300 $^{\circ}$ F), 1400 $^{\circ}$ C (2552 $^{\circ}$ F), 1430 $^{\circ}$ C (2606 $^{\circ}$ F)

CCEWOOL® Ceramic Fiber Paper is produced from high-purity refractory ceramic fibers along with a small amount of binder through a nine-step slag removal process. The product possesses excellent thermal insulation and construction properties, making it highly suitable for deep processing (such as multi-layer composites, punching, etc.) for applications including

high-temperature insulation, thermal insulation, sealing, electrical insulation, sound absorption, filtration, and more. Its exceptional resistance to molten metal penetration allows the product to be used as casting gaskets for isolation in the construction and glass industries. Refractory ceramic fiber paper is available in thicknesses ranging from 0.5 to 12mm and can be cut into various sizes and shapes according to customer requirements.

Characteristics:

Low thermal capacity;

Low thermal conductivity;

Excellent electrical insulation properties;

Excellent machining performance;

High strength, tear resistance;

High flexibility;

Low shot content.

Application:

Automotive and aerospace heat shields;

Gaskets for ovens, stoves, heaters and other appliances;

Automotive muffler insulation;

Investment casting mold wrap;

Expansion joints filling material;

Insulation material for instruments and heating element.

TDS

100			
CCEWOOL® Ceramic Fiber Paper			
Item	1260S	1400	1430HZ
Operation Temperature	1050℃(1922℉)	1200℃(2192 ℉)	1350°C(2462°F)
Density (kg/m3)		180-200	
Tensile Strength (PSI)	58	94	136

salesusa@ccewool.comwww.ccewool.com

Linear Shrinkage (%)			
®1000C,24hrs	2	-	-
®1100C,24hrs	-	2	-
®1200C,24hrs	-	-	2
Lose on ignition (%)	9	9	9
Chemical Composition (%)			
Al2O3	42-47	52-55	39-40
Al2O3+SiO2	97	99	-
ZrO2	-	-	15-17
Fe2O3	1	0.2	0.2
Na2O+K2O	0.5	0.2	0.2
	60000*610*1;30000*610*2		
Specification (MM)	20000*610*3;15000*610*4		
	12000*610*5;10000*610*6		
	Min Width: 5cm		
Package	Inner Plastic Bag +Outer Carton		

CCEWOOL® Intumescent Ceramic Fiber Paper



Temperature Grade 1260 $^{\circ}$ C (2300 $^{\circ}$ F) CCEWOOL® Intumescent Ceramic Fiber Paper is produced from a mixture of high purity refractory ceramic fiber, natural graphite fine flakes, and organic binders through a fiber washing process. At about 1200 $^{\circ}$ F (649 $^{\circ}$ C), CCEWOOL® Intumescent Ceramic Fiber Paper expands up to maximum of 400% of its thickness. This feature serves as excellent material for gasket and sealing applications.

Characteristics:

Low thermal capacity;
Low thermal conductivity;
Excellent electrical insulation properties;
Excellent machining performance;
High strength, tear resistance;
High flexibility;
Low shot content.





salesusa@ccewool.comwww.ccewool.com

Application:

High temperature gasket and seals;

Expansion joints insulation material;

Fire proof;

Seals for industrial furnaces.

TDS

CCEWOOL® Intumescent (Ceramic Fiber Paper	
Color	Gray	
Maximum temperature rating ℃	1260(2300°F)	
Continuous use limit ℃	1050(1922°F)	
Melting point [°] C	1700(3092°F)	
Chemical Content		
Silica,SiO ₂	45-48	
Alumina Oxide,Al ₂ O ₃	42	
Carbon, C	10-15	
Other	2	
Organic Binder	5-10	
Tensile Strength		
16-18 pcf. density	0.5-0.7 Mpa	
Expansion,%increase		
®400 °F	90(from 3mm thickness)	
®1800°F	420(from 3mm thickness)	
®1800°F	320(from 3mm thickness)	
Sizes Available	610/1220mm	
Thickness	2-5mm	

CCEWOOL® Ceramic Fiber Retardant Paper



Temperature degree: 1260° C (2300°F), 1400° C (2550°F), 1430° C(2600°F)

CCEWOOL® ceramic fiber retardant paper is a new research of our company. Up to now, it is the only product which doesn't get burnt when contact fire in ceramic fiber paper field. By adding certain proportion fire retardants into



www.ccewool.com

ceramic fiber paper's composition, the paper can be directly contact with fire and won't get burnt.

Characteristics:

retardant
Low thermal capacity
Low thermal conductivity
Excellent electrical insulation properties
Excellent machining performance
High strength, tear resistance
High flexibility
Low shot content

Applications:

Industrial insulation, sealing, anti-corrosion material
Insulation material for instruments and heating element
Insulation material for automobile and aerospace industry
Expansion joints filling material
Isolation for construction material, metallurgy and glass industries,
Molten metal sealing gasket
Fireproof material

TDS

CCEWOOL® Ceramic fiber retardant paper			
Item	1260STD	1400HA	1430HZ
Operation Temperature	1050 ℃	1200℃	1350℃
Density (kg/m3)	180-200		
Tensile Strength (PSI)	58	94	136
Linear Shrinkage (%)			
@1000C,24hrs	2	-	-
@1100C,24hrs	-	2	-
@1200C,24hrs	-	-	2
Lose on ignition (%)	9	9	9
Chemical Composition (%)			
Al2O3	46	52-55	39-40
Al2O3+SiO2	97	99	-
ZrO2	-	-	15-17
Fe2O3	1	0.2	0.2
Na2O+K2O	0.5	0.2	0.2



CCEWOOL Thermomax Inc.

salesusa@ccewool.comwww.ccewool.com

Specification (MM)	60000*610*1;30000*610*2
	20000*610*3;15000*610*4
	12000*610*5;10000*610*6
	Min Width: 5cm
Package	Inner Plastic Bag +Outer Carton