

CCEWOOL® Low Biopersistent Fiber Paper



Temperature Grade: 1200 °C (2192 °F)

CCEWOOL® Low Biopersistent Fiber

Paper is made from alkaline-earth silicate fibers primarily composed of SiO₂, MgO, and CaO, blended with specific organic binders. This soluble fiber product is an innovative solution for high-temperature applications. With its unique calcium-magnesium chemical composition, it meets the requirements of

applications up to 1200 °C (2192 °F) while also demonstrating significant solubility and environmental-friendly characteristics. We offer soluble fiber paper in thicknesses ranging from 0.5 to 12mm. The product's safe operating temperature reaches up to 1200 °C.

Characteristics:

- Low bio-persistence fibre;
- Excellent thermal insulating performance;
- Thin, flexible high-temperature insulation;
- Immune to thermal shock;
- Low heat storage;
- Easily die-cut to form complex shapes for high-temperature gasketing;
- Excellent tensile strength;
- Low thermal conductivity;
- Non-wetting to molten aluminium.

Application:



High temperature gasket and sealing in various application;

Fire proof;

Fireproof doors;

Expansion joints ;

Fireplace converter gasket;

Gasket between Aluminum and zinc washer

- High temperature gaskets
- Metal lining;

Melting and holding furnaces refractory backing;

TDS

CCEWOOL® Low Biopersistent Fiber Paper	
Classification temperature	1200 °C (2192°F)
Density, Kg/m3	190-210
Operation temperature	1000°C (1832°F)
Melting point	>1300°C (2372°F)
Tensile strength(Kpa)	>250
Loss on ignition (wt%)	9
Permanent Linear shrinkage, % ENV(1094-1)	
After 24 hours @1000°C	1.5
Thermal conductivity (%)	
400°C	0.1
600°C	0.16
800°C	0.22
Chemical composition (%)	
SiO2	65-68

	CaO+MgO	27-33
	others	<=3%
Specification (MM)		60000*610*1;30000*610*2
		20000*610*3;15000*610*4
		12000*610*5;10000*610*6
		Min Width: 5cm
Package		Inner Plastic Bag+Outer Carton

