salesusa@ccewool.comwww.ccewool.com

## **CCEWOOL® Polycrystalline Wool Fiber Paper**



Temperature Grade 1600 ℃ (2912 ℉)

CCEWOOL® Polycrystalline Wool Fiber

Paper is designed for high temperature

applications up to 1600 °C. Manufactured

from high purity Alumina fibres, using

advanced production techniques to ensure

uniform fibre distribution and close control

of thickness and density.

CCEWOOL® Polycrystalline Wool Fiber

Paper is produced using Alumina fibres with the minimum addition of carefully selected bonds, which burn out in service. The ultra-clean 'shot' free properties of the product promote excellent handling and strength characteristics. CCEWOOL® Polycrystalline Wool Fiber Paper has significant benefits as a separating and parting media for vacuum brazing applications and heat treatment. Other applications include gaskets and seals in furnaces with reducing atmospheres and hot isostatic pressing.

## **Characteristics:**

Almost no shot, white color, and high purity of raw materials;

Good high temperature resistance and good high-temperature stability;

Extremely low thermal conductivity, low linear shrinkage after heating;

Stable chemical properties and strong corrosion resistance;

Uniform fiber diameter and high tensile strength;

Excellent thermal stability and thermal shock resistance;

Excellent chemical stability.

## **Application:**

Expansion joints in industrial furnace linings;

salesusa@ccewool.comwww.ccewool.com

Strips in new fiber module lining overcome shrinkage;

Gap filling for lining maintenance/repair;

High Temperature Gaskets and Seals.

## **TDS**

| CCEWOOL® Polycrystalline Wool Fiber Paper |              |
|---|--------------|
| Typical Chemical Analysis (fibre wt. %)   |              |
| Al2O3                                     | 95–97        |
| SiO2                                      | 3–5          |
| Trace                                     | <0.5         |
| Physical Properties                       |              |
| Colour                                    | White        |
| Classification Temperature (°C)*          | 1600(2912°F) |
| Product Density (kg/m3)                   | 160          |
| Product Thickness (mm)+                   | 8            |
| Loss on Ignition (wt. %)                  |              |
| from Fibre                                | 0            |
| from Felt                                 | <12          |