

CCEWOOL® Low Biopersistent Fiber Textiles



Temperature Grade: 1200°C (2300°F)
CCEWOOL® Low Biopersistent Fiber Textiles are made from soluble fibers combined with glass filament or stainless steel wire. Soluble fiber products are an innovative solution for high-temperature applications. Based on their unique chemical composition with calcium and magnesium, they can meet the demands

of 1200°C usage while maintaining significant solubility and environmental characteristics. CCEWOOL® Low Biopersistent Fiber Textiles exhibit excellent chemical stability, remaining unaffected by most chemicals except for hydrofluoric acid, phosphoric acid, and concentrated alkalis. Even when exposed to water or steam, their thermal and physical properties remain unaffected after drying. They possess a solubility certificate from the European Fraunhofer Laboratory.

Characteristics:

- Low thermal conductivity
- Excellent thermal shock resistance, thermal stability
- Excellent tensile strength
- Sound insulation
- Easy cut and easy stall
- Containing no asbestos
- Chemical corrosion resistance.

Applications:

- Furnace door insulation and sealing
- Filling expansion joints in boilers and kilns
- Coke oven door frame sealing
- High-temperature gaskets and packaging
- Expansion joint filling
- Heat treatment furnace for wrapping radiation tubes
- Coating between reinforcement and casing to prevent molten liquid leakage

TDS

Description	CCEWOOL® Low Biopersistent Fiber Textiles					
	Cloth		Tape		Yarn	
Reinforcement	Glass Fiber	Stainless Steel	Glass Fiber	Stainless Steel	Glass Fiber	Stainless Steel

Continuous Temperature Use Limit (°C)	650	1000	650	1000	650	1000	
Color	Light Bluish		Light Bluish		Light Bluish		
Density (kg/m ³)	500		550-600		-		
Organic Content (%)	≤18		≤18		≤18		
Description	CCEWOOL® EcoFiber Textiles						
	Round Braided Rope		Square Braided Rope		Twisted Rope		Woolen Rope
Reinforcement	Glass Fiber	Stainless Steel	Glass Fiber	Stainless Steel	Glass Fiber	Stainless Steel	Glass Fiber
Continuous Temperature Use Limit (°C)	650	1000	650	1000	650	1000	650
Color	Light Bluish		Light Bluish		Light Bluish		Light Bluish
Density (kg/m ³)	550-600		550-600		550-600		550-600
Organic Content (%)	≤18		≤18		≤18		≤18

CCEWOOL® Ceramic Fiber Yarn



Temperature Grade: 1260°C (2300°F)
CCEWOOL® Ceramic Fiber Yarn is made through a special process using refractory ceramic fiber cotton, non-alkali glass filament, and high-temperature-resistant stainless steel alloy wire. It is used for the installation of insulation materials and heat conduction systems and is also widely used in the production of other refractory ceramic

fiber textiles. Products made from CCEWOOL® Ceramic Fiber Yarn are sturdy, chemically stable, and have excellent insulation qualities.

Characteristics:

Excellent high-temperature strength;
Excellent electrical insulating properties;

Excellent resistance to acid, oil, water vapor corrosion;
Low thermal conductivity;
Excellent thermal insulation.

Application:

Stitching fireproof cloth/tape/rope

TDS

CCEWOOL® Ceramic Fiber Yarn		
Classification Temperature (°C)	1260 (2300°F)	
Name	Glass Filament Reinforced Yarn	Inconel Wire Reinforced Yarn
Density (kg/m ³)	550	
Long-term Operation Temp (°C)	550	1050
Water Content(%)	≤2	
Organic Content (%)	≤15	
Shrinkage at 982°C (%)	-1%	
Packing of ceramic fiber yarn	Braided Bag/ Carton	

CCEWOOL® Ceramic Fiber Cloth



Temperature Grade: 1260°C (2300°F)

CCEWOOL® Ceramic Fiber Cloth is woven from high-quality refractory ceramic fiber yarn and is a high-performance industrial-grade refractory ceramic fiber fabric suitable for high-temperature applications. It is lightweight, flexible, and available in various thicknesses, widths, and densities. CCEWOOL® Ceramic Fiber Cloth contains a certain amount of organic fibers, which gradually carbonize and turn black when heated, without affecting its normal insulation performance. As the temperature continues to rise, the product will gradually turn white

again as the organic fibers are completely carbonized. It is available in two variations, reinforced with either nickel-chromium alloy wire or glass filament, and it has excellent wear resistance and resistance to

mechanical damage, maintaining high strength at high temperatures. CCEWOOL® Ceramic Fiber Cloth is easy to manufacture, has low shrinkage, and remains flexible even after exposure to high temperatures.

Characteristics:

- Low thermal conductivity
- Excellent thermal shock resistance, thermal stability
- Excellent tensile strength
- Sound insulation
- Easy cut and easy stall
- Containing no asbestos
- Chemical corrosion resistance.

Application:

- Gasket and wrapping material
- Induction heating furnace coil insulation
- Cable and wire insulation (thermal and/or electrical)
- Infrared radiating diffusers
- Boiler tadpole gaskets
- Fuel line insulation
- Furnace heat zone separators
- Exhaust hood curtains
- Pipe hanger insulation

TDS

CCEWOOL® Ceramic Fiber Cloth		
Classification Temperature (°C)	1260 (2300°F)	
Name	Glass Filament Reinforced Cloth	Inconel Wire Reinforced Cloth
Density (kg/m ³)	550	
Long-term Operation Temp	550	1050
Water Content	≤2	
Organic Content (%)	≤15	
Shrinkage at 982°C (%)	-1	
Packing of ceramic rope	Braided Bag/ Carton	
Specification (T x W x L)	2mm x 1m x 30m (1/12" x 40" x 100')	
	3mm x 1m x 30m (1/8" x 40" x 100')	
	5mm x 1m x 20m (1/5" x 40" x 66')	
	6mm x 1m x 20m (1/4" x 40" x 66')	

CCEWOOL® Ceramic Fiber Tape



Temperature Grade: 1260°C (2300°F)
CCEWOOL® Ceramic Fiber Tape is made from high-quality refractory ceramic fiber yarn, reinforced with either glass filament or stainless steel wire. It possesses excellent chemical stability, outstanding resistance to thermal shock, corrosion resistance, and resistance to damage caused by mechanical vibrations and stress. It is highly suitable for industrial applications that require sturdy, flexible, and high-temperature-resistant materials. CCEWOOL® Ceramic Fiber Tape is used in various thermal equipment and heat conduction systems for fire

resistance, insulation, and friction applications.

Characteristic:

- Low thermal conductivity
- Excellent thermal shock resistance, thermal stability
- Excellent tensile strength
- Sound insulation
- Easy cut and easy stall
- Containing no asbestos
- Chemical corrosion resistance

Application:

Industrial thermal insulation, pipe and cable insulation coating, exhaust piping insulation coating, bolt flange connection, thermal radiation shielding, high temperature furnace door curtain

TDS

CCEWOOL® Ceramic Fiber Tape		
Classification Temperature (°C)	1260 (2300°F)	
Name	Glass Filament Reinforced Tape	Inconel Wire Reinforced Tape
Density (kg/m ³)	550	
Long-term Operation Temp	550°C	1050°C
Water Content (%)	≤2	
Organic Content (%)	≤15	
Shrinkage at 982°C (%)	-1	
Packing of ceramic tape	Braided Bag/ Carton	
Specification	2mm x 20mm x 30m (1/12" x 4/5" x 100')	

(T x W x L)	3mm x 20mm x 30m (1/8" x 4/5" x 100')
	2mm x 30mm x 30m (1/12" x 6/5" x 100')
	3mm x 30mm x 30m (1/8" x 6/5" x 100')
	2mm x 40mm x 30m (1/12" x 8/5" x 100')
	3mm x 40mm x 30m (1/8" x 8/5" x 100')
	2mm x 50mm x 30m (1/12" x 2" x 100')
	3mm x 50mm x 30m (1/8" x 2" x 100')
	2mm x 60 mm x 30m (1/12" x 12/5" x 100')
	3mm x 60 mm x 30m (1/8" x 12/5" x 100')
	2mm x 75 mm x 30m (1/12" x 3" x 100')
	3mm x 75 mm x 30m (1/8" x 3" x 100')
	2mm x 80 mm x 30m (1/12" x 16/5" x 100')
	3mm x 80 mm x 30m (1/8" x 16/5" x 100')
	2mm x 100 mm x 30m (1/12" x 4" x 100')
	3mm x 100 mm x 30m (1/8" x 4" x 100')
	2mm x 150 mm x 30m (1/12" x 6" x 100')
3mm x 150 mm x 30m (1/8" x 6" x 100')	

CCEWOOL® Ceramic Fiber Rope



Temperature Grade: 1260°C (2300°F)

CCEWOOL® Ceramic Fiber Rope is a series of dense and resilient refractory ceramic fiber materials made from high-quality refractory ceramic fiber cotton as raw material, combined with lightweight yarn and woven through a special process. Depending on different temperature requirements and applications, it may include reinforced materials like glass filament or heat-resistant alloy steel wire. It is widely used in various high-temperature gasket, packing, and sealing applications, particularly suitable for

high-temperature and high-pressure mechanical sealing in pumps and valves. CCEWOOL® Ceramic Fiber Rope boasts excellent chemical stability, with the ability to resist most corrosive agents, as well as oxidation and reduction. Even if it gets wet with water or steam, its thermal and physical properties fully recover after drying.

Characteristics:

Low thermal conductivity

Excellent thermal shock resistance, thermal stability

Excellent tensile strength

Sound insulation

Easy cut and easy stall

Containing no asbestos

Chemical corrosion resistance.

Application:

Furnace doors insulation and seals

Expansion joint filling in furnace and boiler

Coke oven door seals

High temperature gasket and packing

Radiant tube packing heat treatment furnace

Packed between steel bar and tube to avoid leakage of melting liquid

TDS

CCEWOOL® Ceramic Fiber Rope		
Classification Temperature (°C)	1260 (2300°F)	
Name	Glass Filament Reinforced Rope	Inconel Wire Reinforced Rope
Density (kg/m ³)	550	
Long-term Operation Temp	550	1050
Water Content	≤2	
Organic Content (%)	≤15	
Shrinkage at 982°C (%)	-1	
Size (diameter) (mm)	6-120 (1/4"-24/5")	
Packing of ceramic rope	Braided Bag/ Carton	

