

CCEWOOL® Polycrystalline Wool Fiber Paper



Temperature Grade 1600°C (2912°F)

CCEWOOL® Polycrystalline Wool Fiber Paper is designed for high temperature applications up to 1600°C. Manufactured from high purity Alumina fibres, using advanced production techniques to ensure uniform fibre distribution and close control of thickness and density.

CCEWOOL® Polycrystalline Wool Fiber

Paper is produced using Alumina fibres with the minimum addition of carefully selected bonds, which burn out in service. The ultra-clean 'shot' free properties of the product promote excellent handling and strength characteristics. CCEWOOL® Polycrystalline Wool Fiber Paper has significant benefits as a separating and parting media for vacuum brazing applications and heat treatment. Other applications include gaskets and seals in furnaces with reducing atmospheres and hot isostatic pressing.

Characteristics:

- Almost no shot, white color, and high purity of raw materials;
- Good high temperature resistance and good high-temperature stability;
- Extremely low thermal conductivity, low linear shrinkage after heating;
- Stable chemical properties and strong corrosion resistance;
- Uniform fiber diameter and high tensile strength;
- Excellent thermal stability and thermal shock resistance;
- Excellent chemical stability.

Application:

- Expansion joints in industrial furnace linings;



Strips in new fiber module lining overcome shrinkage;

Gap filling for lining maintenance/repair;

High Temperature Gaskets and Seals.

TDS

CCEWOOL® Polycrystalline Wool Fiber Paper	
Typical Chemical Analysis (fibre wt. %)	
Al ₂ O ₃	71-73
SiO ₂	27-29
Trace	<0.5
Physical Properties	
Colour	White
Classification Temperature (°C)*	1600(2912°F)
Product Density (kg/m ³)	160
Loss on Ignition (wt. %)	
from Fibre	0
from Felt	<12

