

CCEWOOL® Low Biopersistent Fiber Module



Temperature Grades: 1200°C (2192°F),

1300°C(2372°F)

CCEWOOL® Low Biopersistent Fiber

Module is compressed from soluble fiber blankets. Low Biopersistent Fiber products are innovative solutions for high-temperature applications. Based on the unique characteristics of its

calcium-magnesium chemical composition, it can meet the requirements of use up to 1300°C (2372°F) while also exhibiting significant solubility and environmental properties. This module is designed to meet the insulation needs of industrial furnaces under specific thermal conditions. The bio-soluble fiber modules are produced with various anchoring systems for quick, easy, and efficient installation in most furnace linings. Module linings can improve furnace productivity and reduce maintenance costs.

Characteristics:

High temperature stability (up to 1300° C);

Low thermal conductivity;

Thermal shock resistance;

Low heat storage;

Lightweight;

Fast installation & selection of attachment systems.

Application:

Heat treatment and forge furnaces;

Annealing furnaces;

Process heaters;



Ceramic tunnel kilns and Intermittent kilns;

Stress relieving furnaces;

Door and cover linings;

Carbottom heating furnaces;

Stack, flue and duct linings;

Incinerators and boilers;

Ladle preheat stands.

TDS

CCEWOOL® Low Biopersistent Fiber Module		
Classification Temperature (°C)(°F)	1200°C(2192°F)	1300°C(2372°F)
Chemical Composition (%)		
SiO ₂	62-68	≥70
CaO	26-32	-
MgO	4-7	-
CaO+MgO	-	≥20
Color	Light Bluish	Light Bluish
Density (kg/m ³)(lb/ft ³)	160-220(10-13.75)	160-220(10-13.75)
Permanent Linear Shrinkage (%)	1200°C x 24h ≤1.0	1300°C x 24h ≤3.0
Thermal Conductivity (W/m·K)		
400°C	0.07	0.07
600°C	0.11	0.13
800°C	0.17	0.2
1000°C	0.23	0.3
1200°C	-	0.41